

WPL Wire Pulling Lubricant

Data Sheet

1. Product Description

WIRE LUBE wire Pulling Lubricant is a translucent white polymer gel which produces a low coefficient of friction for smooth, low tension wire and cable pulling. A low coefficient of friction makes cable pulling easier and safer with less chance for cable jacket damage from high pulling forces. The lubricant is easy to handle and apply. The material is colorless and non-staining and affords quick and easy cleanup. The low solids content means less conduit blocking if additional pulls are required. The WIRE LUBE Wire Lubricant is available in four sizes.

WPL 3377 1 L
WPL 4049 1 GALLON
WPL 9988 20 L

Wire Pulling Lubricant Features

- UL Listed File E162404
- CSA Certified File LR108775
- Versatile (compatible with a wide range of cable types and jacket materials).
- Temperature stable. The lubricant can endure freezing and high temperature storage conditions and will not phase separate.
- Colorless, not-staining and is easy to cleanup.
- Low coefficient of friction.
- Low solids content. < 3.5% solids.
- Does not contain any wax, grease or silicone.

2. Applications

Wire Lube Wire Pulling Lubricant is suitable for pulling a wide variety of cable types, such as power, control, instrumentation and communication cables. This includes coaxial and fiber optic cables. This lubricant is compatible with common types of cable jacket materials.

3. Data: Physical Properties

Thixotropic translucent gel

Percent non-volatile solids: 2.5-3.5%

pH: 6.5-8.5

Temperature use range: 20°F - 110°F

Temperature stability:

< 10% change in Brookfield viscosity from 40°F to 100°F.
No separation after five freeze/thaw cycles or 24 hours at 120°F.

Flammability: No flash point.

Lubricity:

- PVC or XLP jacketed cable on PVC conduit at 200 lbs/ft; coefficient of dynamic friction < 0.11, coefficient of static friction < 0.13.
- PVC or XLP jacketed cable on EMT conduit at 200 lbs/ft normal pressure; coefficient of dynamic friction < 0.18, coefficient of static friction < 0.20.

Lubricity of Dried Residue:

- PVC or XLP jacketed cable on PVC conduit at 200 lbs/ft normal pressure; coefficient of dynamic friction < 0.15, coefficient of static friction < 0.20.
- PVC or XLP jacketed cable on EMT conduit at 200 lbs/ft normal pressure; coefficient of dynamic friction < 0.13, coefficient of static friction < 0.17.

Polyethylene Stress Cracking: None / ASTM D1693

Compatible with conductive polymeric insulation's shields and jackets

IEEE P1026

4. Specifications

Product

The lubricant shall be a polymer gel capable of use from 20°F to 110°F and storage at subfreezing or high temperature warehouse conditions without phase separation. The wire pulling lubricant must produce a low coefficient of friction when pulling a variety of cable types and have no adverse effects on the physical or electrical properties of cable jackets or semi-conducting shielding material. The lubricant must be colorless and non-staining. The gel must have no flash point. Lubricant shall be UL Listed and CSA Certified.

Engineering Specifications

The wire pulling lubricant shall be Wire Lube WL Wire Pulling Lubricant. The lubricant shall be a polymer gel type material and must be compatible with a wide variety of cable jacketing materials. The lubricant must be colorless and non-staining. The lubricant shall be unaffected by normal warehouse storage conditions.

5. Installation Techniques

The lubricant needs to reach all points where the cable and conduit rub together to obtain optimum tension reduction. Normal application is by wiping on the cable jackets as the

cable is pulled into the conduit. The cable will generally carry enough lubricant to complete an average pull. If cable pulls are long or difficult, inject the lubricant directly into the conduit and spread ahead of the cable in addition to wiping on the jackets.

The amount of lubricant needed can vary greatly depending on the difficulty of the pull. A general formula to determine application rates for a normal pull is: Quantity (gallons) = .0015 x L x D. Where L equals length of pull in feet and D equals diameter of conduit in inches. For example, approximately 3/4 gallon per 100' of 5" conduit.

6. Maintenance

Wire Lube WL Wire Pulling Lubricant is unimpaired by normal warehouse storage conditions. Opened containers should be tightly resealed to prevent evaporation of the material.

7. Availability

Wire Lube WPL Wire Pulling Lubricant is available in 1 quart squeeze bottles or 1 gallon 20 L from electrical distributors. Fifty-five-gallon drums may be special ordered. Material Safety Data Sheets (MSDS) are available from Wire Lube or your electrical distributor.

IMPORTANT NOTICE

Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use.

Warranty; Limited Remedy; Limited Liability. This product will be free from defects in material and manufacture as of the date of purchase. Wire Lube **MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** If this product is defective within the warranty period stated above, your exclusive remedy shall be, at Wire Lube's option, to replace or repair the Wire Lube product or refund the purchase price of the Wire Lube product. **Except where prohibited by law, Wire Lube will not be liable for any loss or damage arising from this Wire Lube product, whether direct, indirect, special, incidental or consequential regardless of the legal theory asserted.**